Appl. No.: 10/658,448

TC/A.U.: 3711 Docket No.: B03-57 Reply to Office Action of April 7, 2004

LISTING OF CLAIMS

Please amend the claims as follows:

- (Original) A golf ball comprising: 1.
 - a core having a Shore C hardness of about 70 or less, the core comprising at least a core layer comprising:

an elastomeric composition,

a reactive co-agent present by less than about 10 phr by weight of the elastomeric composition, and

a cross-linking agent;

at least a first intermediate layer encasing the core, the first intermediate layer having a Shore C hardness of about 70 to about 75; and

a cover encasing the first intermediate layer, the cover having a Shore C hardness of about 60 or less.

- (Original) The golf ball of claim 1, wherein the elastomeric composition comprises a diene 2. polymer.
- (Original) The golf ball of claim 2, wherein the cross-linking agent is a peroxide. 3.
- (Original) The golf ball of claim 3, wherein the diene polymer is a polybutadiene. 4.
- (Original) The golf ball of claim 2, wherein the cross-linking agent is sulfur. 5.
- (Original) The golf ball of claim 5, wherein the diene polymer is an ethylene-propylene-6. diene polymer.
- (Original) The golf ball of claim 6, wherein the ethylene-propylene-diene polymer 7. comprises about 70% to about 90% ethylene.

Appl. No.: 10/658,448 TC/A.U.: 3711 Docket No.: B03-57 Reply to Office Action of April 7, 2004

- 8. (Original) The golf ball of claim 7, wherein the ethylene-propylene-diene polymer further comprises about 1% to about 5% ethylidene-2-norborene.
- 9. (Original) The golf ball of claim 1, wherein the elastomeric composition comprises a material selected from a group consisting of metallocene catalyzed polymers, poly(styrene-butadiene-styrene), SEBS, SEPS block polymers, styrene-ethylene block copolymers, and polar group grafted or copolymerized polymers.
- 10. (Original) The golf ball of claim 1, wherein the reactive co-agent is present by less than about 5 phr.
- 11. (Amended) The golf ball of claim 1, wherein the reactive co agent is present by about 0 phr
 A golf ball comprising:
 - a core having a Shore C hardness of about 70 or less, the core comprising at least a core layer comprising:

an elastomeric composition,

about 0 phr of reactive co-agent by weight of the elastomeric composition, and a cross-linking agent;

at least a first intermediate layer encasing the core, the first intermediate layer having a Shore C hardness of about 70 to about 75; and

a cover encasing the first intermediate layer, the cover having a Shore C hardness of about 60 or less.

- 12. (Original) The golf ball of claim 1, wherein the reactive co-agent comprises a metal salt of diacrylate, dimethacrylate, or monomethacrylate, or a non-metallic oligomer.
- 13. (Original) The golf ball of claim 12, wherein the metal is selected from zinc, magnesium, calcium, barium, tin, aluminum, lithium, sodium, potassium, iron, zirconium, and bismuth.
- 14. (Original) The golf ball of claim 1, wherein the core further comprises an innermost core encased by the core layer.

Appl. No.: 10/658,448 TC/A.U.: 3711 Docket No.: B03-57 Reply to Office Action of April 7, 2004

- (Original) The golf ball of claim 14, wherein the innermost core comprises a diene polymer 15. and about 10 phr to about 50 phr of a reactive co-agent.
- (Original) The golf ball of claim 14, wherein the innermost core comprises a diene polymer 16. and at least about 50 phr of a reactive co-agent.
- (Original) The golf ball of claim 1, wherein the golf ball further comprises a second 17. intermediate layer encasing the first intermediate layer, the second intermediate layer being harder than the first intermediate layer, and having a Shore C hardness of about 72 to about 77.
- (Original) The golf ball of claim 17, wherein the golf ball further comprises a third 18. intermediate layer encasing the second intermediate layer, the third intermediate layer being harder than the second intermediate layer, and having a Shore C hardness of about 75 to about 80.
- (Original) The golf ball of claim 18, wherein the first, second, and third intermediate layers 19. each has a thickness of less than about 2.54 mm.
- (Original) The golf ball of claim 18, wherein the first, second, and third intermediate layers 20. each has a thickness of less than about 1.27 mm.
- (Original) The golf ball of claim 18, wherein the first, second, and third intermediate layers 21. each has a thickness of about 0.76 mm to about 1.27 mm.
- (Original) The golf ball of claim 1, wherein the core has a diameter of about 31.75 mm to 22. about 40,64 mm.
- 23. (Cancelled).
- 24. (Cancelled).
- 25. (Cancelled).

Appl. No.: 10/658,448 TC/A.U.; 3711 Docket No.: B03-57 Reply to Office Action of April 7, 2004

- 26. (Cancelled).
- 27. (Cancelled).
- 28. (Cancelled).
- 29. (Cancelled).
- 30. (Cancelled).
- 31. (Cancelled).
- 32. (Cancelled).
- 33. (Cancelled).
- 34. (Cancelled).
- 35. (Cancelled).
- 36. (Cancelled).
- 37. (Cancelled).
- 38. (Cancelled).
- 39. (Cancelled).
- 40. (Cancelled).
- 41. (Cancelled).

Appl. No.: 10/658,448 TC/A.U.: 3711 Docket No.: B03-57 Reply to Office Action of April 7, 2004

- 42. (Cancelled).
- 43. (Cancelled).
- 44. (Cancelled).